



EPDM-FDA E132 – white (sulphur cross linked)

General

E132-W85 is a white Ethylene Propylene Rubber, commonly referred to as EPDM. This material is often used in hot water steam applications as well as in fire resistant fluids where synthetic oils are used. EPDM materials are also used in bases, acids and alcohols. EPDM is also used for brake fluids, but we recommend observing local safety-regulations before installing an EPDM seal in braking systems. EPDM is not resistant to mineral- vegetable- and animal oils. EPDM-FDA E132 – white is approved for the use of applications in contact with foodstuff.

Physical properties

Density:	DIN ISO 1183-1	g/cm ³	1,39	±0,03
Hardness at 23°C:	DIN ISO 7619-1	Shore A	85	±5
100% Modulus:	DIN 53504	N/mm ²	3,0	*
Tensile strength:	DIN 53504	N/mm ²	5,8	*
Elongation at break:	DIN 53504	%	454,5	*
Tear resistance:	DIN ISO 34-1	kN/m	28,8	*
Compression set, 24h, 70°C, 25%:	DIN ISO 815-1	%	19,8	*
Compression set, 24h, 100°C, 25%:	DIN ISO 815-1	%	35,1	*

* mentioned values are subject to a tolerance of +/- 25%

Temperature range: -50°C to 100°C

Chemical resistance

Resistant to: Water up to 90°C, HFC, HFD-R Fluids, Ozone, Oxygen, Alcohols, Ketones, Esters, Air up to 100°C

Not Resistant to: Steam from 180°C, HFA, HFB, HFD-S Fluids, Mineral Oils, Vegetable Oils, Biodegradable Oils, Fuels, Air from 150°C

Main application

Static and dynamic seals (standard and special), wipers, O-rings, flange seals, rotary seals, rubber energizers (preload elements); cleaning and washing technology; applications in the food industry.

Available certificates

Conform to (EC) No 1935/2004 on materials and articles intended to come into contact with food

Conform to positive list of FDA 21 CFR 177.2600

Analysis and Evaluation

Values mentioned above are based on several tests performed during development and production of the material. Tests have been performed on standard test pieces specified within the relevant standard within the laboratory. Tests performed on any other pieces which are not related to the corresponding standard or made out of any (semi)finished part or any other part deviating in production process, dimension or age of the material from above may result in different values. The data represent our present empirical values and do not disengage the processor or user from his obligation to examine the usage of the material for his specific application.

HYDROMARK LTD., Tsar Osvoboditel 315 blvd. ,Varna 9023, Bulgaria

T: +35952506013, M: +359888837841, E: info@hydromark.eu